



STRATA-FILL™ 24-070

Technical Data Sheet

STRATA-FILL™ Product Line

The Strata-Fill™ light-weight fill product line is comprised of dual-component systems formulated for a variety of geotechnical applications, such as void filling, pipe abandonment, trench breakers, and cavity filling. Each batch goes through stringent testing and quality assurance standards to ensure reliability in the field.

STRATA-FILL™ 24-070

Strata-Fill™ 24-070 is a two-component, HFO blown, low-exotherm polyurethane system. 24-070 offers slow reactivity for greater flow, making it ideal for filling large void areas, pipe abandonment, and underground tank abandonment.

APPLICATIONS

- Filling Large Voids
- Pipe Abandonment
- Underground Tank Abandonment

UNIQUE ADVANTAGES

- Low Exotherm
- Slow Reactivity
- Excellent Flow

REACTIVITY AT 110°F

Cream Time	11 – 13 seconds
Gel Time	147 – 153 seconds
Tack Free Time	245 – 250 seconds
Rise Time	337 – 343 seconds

Chemical Resistance

- Solvents...* **Excellent**
- Mold and Mildew...* **Excellent**

Performance

- Wet Environments...* **Poor**
- Material Flow...* **High**

Physical Properties

Physical Properties	Test Method	Free Rise
Density	ASTM D1622	2.1 pcf
Compressive Strength	ASTM D1621	30.9 psi
Compressive Modulus	ASTM D1621	744 psi
Tensile Strength	ASTM D1623	52 psi
Tensile Modulus	ASTM D1623	86 psi
Water Absorption	ASTM D2842	≤0.04 lbs/ft ²
Closed Cell Content		>90%
Max Service Temp		200°F
Elongation	ASTM D162.	6%
Shear Strength	ASTM C273	31 psi
Shear Modulus	ASTM C273	200 psi
Flexural Strength	ASTM D790	31 psi
Flexural Modulus	ASTM D790	580 psi

Special Testing/Certifications

Flammability	FMVSS-302 FAR 24.853A(III) UL-94	PASS PASS PASS
USG Title 33, Chapter 1, Part 183		PASS
Initial K-Factor		0.167
Moister Vapor Transmission		2-3 PERM•INCH

Component Properties

Component	B-24-070	A2-000
Appearance	Transparent Liquid	Clear Brown Liquid
Brookfield Viscosity @20rpm	680 cps at 72°F	200 cps at 72°F
Specific Gravity	1.053	1.24
Weight per Gallon	8.79 lbs	10.3 lbs
Storage Temperature	50-100°F	50-100°F

Mix Ratio

By weight... 118 parts A-side: 100 parts B-side

By volume... 100 parts A-side: 100 parts B-side

Processing Parameters

A-side Temperatures	100 – 120°F
B-side Temperatures	100 – 120°F
Mixing Pressure	1000 psi static 800 psi dynamic

Storage and Handling

For optimum shelf life, the recommended storage temperature is 50°F to 100°F. **Do not expose iso to lower temperatures – freezing may occur.** Avoid moisture contamination during storage, handling, and processing. After opening, pad the containers and day tanks with either nitrogen or dry air (desiccant cartridge or air dryer @ -40°F dew point).

Store components at 70°F to 90°F for several days prior to use to minimize viscosity issues.

Shelf life of B-side is 6 months and A-side is 2 years for factory sealed containers.

Application Cautions

Careful consideration should be given to selection and application of any NCFI Polyurethane foam system where excessive foam mass build-up can occur. Excessive polyurethane foam lift thickness will result in high internal temperatures within the injected foam, which can result in degraded foam properties, or in extreme cases, fire or spontaneous combustion. **Any flammability rating contained in this literature is not intended to reflect hazards presented by this or any other material under actual fire conditions.** Each person, firm or corporation engaged in the application, installation or use of any polyurethane product should carefully determine whether there is a potential fire hazard associated with such product in a specific usage and utilize all appropriate precautionary and safety measures. Please consult NCFI Polyurethanes for safety considerations, polyurethane system selection and application recommendations.

The Information contained herein is believed to be reliable, but no representations, guarantees, or warranties of any kind are made as to its accuracy, suitability for particular applications or the results to be obtained there from. The information is based on laboratory work with small-scale equipment and does not necessarily indicate end product performance. Because of the variation in methods, conditions and equipment used commercially in processing these materials, no warranties or guarantees are made as to the suitability of the products for the application disclosed. Full-scale testing and end product performance are the sole responsibility of the user. NCFI Polyurethanes shall not be liable for and the customer assumes all risk and liability of any use or handling of any material beyond NCFI's direct control. NCFI MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OR MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein is to be considered as permission, recommendations, nor as an inducement to practice any patented invention without permission of the patent owner.